

BLASTOX®

TECHNICAL BULLETIN

TB-002/Rev 7-98

LABORATORY TESTING OF SPENT ABRASIVES

The EPA requires either a Toxicity Characteristic Leaching Procedure (TCLP) test or 'generator's knowledge of the waste' to characterize spent abrasives as being hazardous or non-hazardous. Because of disposal costs and potential liabilities of assuming a waste has a specific characteristic, the industry standard practice is to have the spent abrasive tested by TCLP at a qualified laboratory. The outcome of these tests have a significant bearing on subsequent material handling and disposal.

The EPA has outlined a protocol (EPA TCLP Method 1311) specifying the necessary steps for consistent administration of the TCLP test method. Despite this "recipe" for performing the test, laboratories that do not routinely maintain a high frequency of TCLP testing may not produce accurate results every time. Flawed results may cost contractors and generators unnecessary expenses and/or lead to disposal decisions which are not environmentally sound. To minimize potentially flawed results on Blastox® spent abrasives, **the contractor should request the laboratory to report initial pH, pH after hydrochloric acid addition and final pH of extract.**

Before contractors/generators send their spent abrasive for TCLP testing, it is in their best interest to check into the selected laboratory. The selected laboratory should be accredited by American Industrial Hygiene Association (AIHA), or American Association for Laboratory Accreditation (A2LA), or have a comparable state accreditation. The TDJ Group has gone through this selection process and has had what it deemed the most qualified laboratories perform thousands of TCLP tests for general R & D purposes. Because of familiarity with these select laboratories, TDJ is confident in their testing procedures and the accuracy of the test results. A partial list of these laboratories is on page 2.

Also of critical importance are the instructions given to the laboratory on the type of test(s) needed. A **TCLP** test for the heavy metal in question (typically Lead) is the proper test which should be requested to determine if your waste is hazardous or non-hazardous, rather than a **Total Metal** test. A total metal test is usually performed prior to the start up of a project to determine if, and at what percent, lead is present in a particular coating system. A total metal test does not provide data necessary to make a disposal decision.

Please contact Technical Support Manager for The TDJ Group, if you should have questions regarding TCLP testing and/or interpretation of results.



The TDJ Group, Inc.

760-A Industrial Drive
Cary IL 60013
web www.blastox.com

847-639-1113 Phone
847-639-0499 Fax
e mail tdj@blastox.com

005

Partial List Of Laboratories

- I. EMSL Analytical, Inc.
3 Cooper St.
Westmont, NJ 08108
Contact: Paul Nyfield
Phone Number: 800-220-3675 ext. 1254
Accreditation: AIHA ELLAP, NY ELAP

- II. Environmental Monitoring and Technologies, Inc.
8100 North Austin Avenue
Morton Grove, IL 60053-3203
Contact: Keith Gray
Phone Number: 847-967-6666
Accreditation: A2LA Environmental Testing

- III. Corrosion Control Consultants and Labs
4403 Donker Ct.
Kentwood, MI 49512
Contact: Karen Tinklenberg
Phone Number: 616-940-3112
Accreditation: AIHA ELLAP, NY ELAP

- IV. Cirrus Environmental
3130 Skyway Drive, Suite 403
Santa Maria, CA 93455
Contact: Doug Blackburn
Phone Number: 805-346-1766
Accreditation: State Certified

Contractor is required to establish his own account, and should obtain pricing at the time of inquiry. TDJ assumes no responsibility or liability for the use of this information.



The TDJ Group, Inc.

760-A Industrial Drive
Cary IL 60013
web www.blastox.com

847-639-1113 Phone
847-639-0499 Fax
e mail tdj@blastox.com

005